

**TABOREN-PC 42 B 35-630**

Polymer:	PP copolymer
Filler:	Barium Sulphate
Stabilization:	Basic antioxidant
Color:	Blue

Physical Properties:

Properties	Test method	Typical Value ^{*)}	Units
Melt Flow Rate	ISO 1133 230°C, 2.16 kg	1.7	g/10min
Density	ISO 1183-1	1.23	g/cm ³
Tensile Stress at Yield	ISO 527	18	MPa
Flexural Modulus	ISO 178	1`700	MPa
CHARPY Notched Impact Strength	ISO 179-1/1eA 23°C	10.0	kJ/m ²
CHARPY Unnotched Impact Strength	ISO 179-1/1eU 23°C	No Break	kJ/m ²
VICAT Softening Temperature	ISO 306 method A50	145.0	°C

^{*)}The above values are typical for this material, not standardized.

The above details are given to the best of our knowledge and experience but are only meant as suggestions without obligation. Existing third party patent rights must be observed.