

TABOREN-EC 49 C 70

Polymer:	LLDPE
Filler:	Calcium carbonate
Stabilization:	High antioxidant
Color:	Natural

Physical Properties:

Properties	Test method	Typical Value ^{*)}	Units
Melt Flow Rate	ISO 1133 190°C, 2.16 kg	3.5	g/10min
Density	ISO 1183-1	1.66	g/cm ³
Flexural Modulus	ISO 178	1`300	MPa
VICAT Softening Temperature	ISO 306 method A50	103.0	°C
DF test	IPN-ZP300CH3	0.01	Bar/g

^{*)}The above values are typical for this material, not standardized.

The above details are given to the best of our knowledge and experience but are only meant as suggestions without obligation. Existing third party patent rights must be observed.